

HONEYCOMB STRUCTURE

Patent Number: ☐ EP1249262
Publication date: 2002-10-16
Inventor(s): MIYAIRI YUKIO (JP); HARADA TAKASHI (JP)
Applicant(s): NGK INSULATORS LTD (JP)
Requested Patent: JP2001190916
Application Number: EP20010900653 20010111
Priority Number(s): WO2001JP00076 20010111; JP20000005063 20000113
IPC Classification: B01D46/00; B01D53/86; B01J35/04; F01N3/28
EC Classification: B01J35/04, B01D53/88B, F01N3/022B, F01N3/035, F01N3/28B4B
Equivalents: AU2548101, ☐ US2002197193, ☐ WO0151173, ZA200205518
Cited patent(s):

Abstract

Data supplied from the esp@cenet database - I2

Best Available Copy

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 249 262 A1

(12)

EUROPEAN PATENT APPLICATION

published in accordance with Art. 158(3) EPC

(43) Date of publication:
16.10.2002 Bulletin 2002/42

(51) Int Cl.7: **B01D 46/00, B01D 53/86,
B01J 35/04, F01N 3/28**

(21) Application number: 01900653.5

(86) International application number:
PCT/JP01/00076

(22) Date of filing: 11.01.2001

(87) International publication number:
WO 01/051173 (19.07.2001 Gazette 2001/29)

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• **HARADA, Takashi NGK Insulators, Ltd.
Nagoya-city, Aichi 467-8530 (JP)**
• **MIYAIRI, Yukio NGK Insulators, Ltd.
Nagoya-city, Aichi 467-8530 (JP)**

(30) Priority: 13.01.2000 JP 2000005063

(74) Representative: **Paget, Hugh Charles Edward et al
MEWBURN ELLIS
York House
23 Kingsway
London WC2B 6HP (GB)**

(71) Applicant: **NGK INSULATORS, LTD.
Nagoya-City, Aichi Prefecture 467-8530 (JP)**

(54) HONEYCOMB STRUCTURE

(57) This is directed to a honeycomb structure (10) including two or more honeycomb segments (11) having numerous through channels having been partitioned by walls and penetrating in axial direction thereof, the walls for through channels having a filtering function, and one end being clogged at predetermined through channels, and the other end at the remaining ones, and joint layers (12) for joining two or more honeycomb segments (11) each other. It may satisfy at least either that the Young's modulus of material of the joint layer (12) is 20% or less of that of the honeycomb segment (11), or that the material strength of joint layer (12) is lower than that of the honeycomb segment (11). This honeycomb structure shows a less thermal stress during use, has such a durability that no crack is formed, hardly shows a difference in temperature between the central portion and outer peripheral portion, and shows a lower pressure loss of fluid.

FIG. 1 (a)




FIG. 1 (b)




FIG. 1 (c)





FIG. 1 (d)



EP 1 249 262 A1

Description

Technical Field

- 5 [0001] The present invention relates to a honeycomb structure used as a filter which collects and removes particulate matters exhausted in a heat engine such as an internal combustion engine or combustion equipment such as a boiler.

Background Art

- 10 [0002] Conventionally, as a method for collecting and removing particulate matters contained in a dust-containing fluid such as exhaust gas emitted from a diesel engine or the like, there is known the use of a honeycomb structure in which a wall of through channel has a filtering function, one end is clogged for predetermined through channels, and the other end is clogged for the remaining through channels.

- 15 [0003] In the case where such a honeycomb structure is used as a filter for collecting particulate matters in exhaust gas, it is necessary to perform regenerating treatment in which accumulating carbon particulates are burned and removed. At this time, a local increase in temperature is unavoidable, so that a high thermal stress is liable to occur, which poses a problem in that a crack is liable to develop.

- [0004] As measures for reducing the thermal stress occurring in such a structural part, a method in which the structural part is divided into small segments is known. The use of a honeycomb structure for collecting particulates in exhaust gas has already been proposed in JP-A-6-241017, JP-A-8-28246, JP-A-7-54643, JP-A-8-28248, etc.

- 20 [0005] However, even in the examples proposed in the aforementioned patent publications, the effect of reducing stress on segment surface is insufficient, and the problem of crack development cannot be solved completely. Also, there is a problem in that a shift in axial direction occurs between the segments during the use. Although a method in which a holding member is used to prevent the shift in the axial direction has been proposed in JP-A-6-241017, there is a problem of deformation and deterioration of the holding member occurring when the member is subject to high temperatures of exhaust gas.

- [0006] As other measures for reducing thermal stress, there has been proposed a method in which a portion liable to have a relatively low temperature is heated electrically by providing an electric heater between the segments to make the temperature distribution in honeycomb structure uniform. However, this method has a problem of the occurrence of a new thermal stress because a local temperature gradient rather increases in the vicinity of the electric heater.

- 30 [0007] Also, there are a problem in that the ratio of the joint layer between the segments to the cross section is too high, so that the pressure loss of fluid is excessive, which deteriorates the engine performance, and a problem in that the heat capacity is too high, so that the rise in temperature takes much time in the regenerating treatment in which carbon particulates are burned to be removed, which prolongs the time necessary for regenerating treatment.

- 35 [0008] The present invention has been made to solve the above problems, and accordingly an object thereof is to provide a honeycomb structure in which a less thermal stress occurs during the use; durability such that no crack develops is ensured; a difference in temperature between the central portion and the outer peripheral portion is less liable to be produced; the pressure loss of fluid is low; and the time and energy necessary for the rise in temperature at the time of regenerating treatment are less.

40

Disclosure of the invention

- [0009] According to the present invention, there is provided a honeycomb structure including two or more honeycomb segments each of which has a large number of through channels which are partitioned by walls and penetrate in the axial direction, the wall of the through channel having a filtering function, and is constructed so that one end is clogged for predetermined through channels, and the other end is clogged for the remaining through channels, and a joint layer for joining the two or more honeycomb segments to each other, characterized in that at least either that the Young's modulus of material of the joint layer is 20% or less of the Young's modulus of material of the honeycomb segment, or that the material strength of the joint layer is lower than the material strength of the honeycomb segment is satisfied.

- 50 [0010] In the present invention, a portion having an area of at least 30% of the surface area of the honeycomb segment in contact with the joint layer preferably has average surface roughness Ra exceeding 0.4 micron, and the ratio of the total heat capacity of all the joint layers in the honeycomb structure to the total heat capacity of all the honeycomb segments constituting the honeycomb structure is preferably 30% or lower.

- 55 [0011] Further, in the honeycomb structure in accordance with the present invention, it is preferable that a corner portion of a cross-sectional shape of the honeycomb segment in the cross section perpendicular to the through channel of the honeycomb structure be rounded with a radius of curvature of 0.3 mm or larger, or be chamfered 0.5 mm or more.

- [0012] Also, the ratio of the total cross-sectional area of the joint layers to the cross-sectional area of the honeycomb structure in the cross section perpendicular to the through channel of the honeycomb structure is preferably 17% or

lower, and further the ratio of the sum of the cross-sectional areas of the joint layers to the sum of the cross-sectional areas of the walls in the cross section of honeycomb structure perpendicular to the through channel of the honeycomb structure is preferably 50% or lower. Still further, it is preferable that the ratio of the cross-sectional area of joint layer to the cross-sectional area of wall in the cross section of honeycomb structure perpendicular to the through channel of the honeycomb structure be higher in the central portion and be lower on the outer peripheral side.

[0013] As a material of the honeycomb segment, one kind of material selected from a group consisting of cordierite, SiC, SiN, alumina, mullite, and lithium aluminum silicate (LAS) is preferably used as a main crystal phase from the viewpoint of strength, heat resistance, and the like.

[0014] Also, it is preferable that the honeycomb segment carry a metal having a catalytic function so as to be used to purify exhaust gas from a heat engine or combustion equipment or to reform a liquid fuel or a gas fuel. As the metal having a catalytic function, at least one kind of Pt, Pd, and Rh is preferably used.

[0015] Further, the cross-sectional shape of the through channel in the honeycomb structure is preferably any of triangle, quadrangle, and hexagon.

Brief Description of the Drawings

[0016]

Figures 1(a), 1(b), 1(c) and 1(d) are explanatory views showing various division patterns of honeycomb segment of a honeycomb structure in accordance with the present invention.

Figure 2 is a partially enlarged view showing a cell construction of a honeycomb structure.

Figure 3 is a sectional view for illustrating one example of a honeycomb structure.

Figure 4 is a partially enlarged view showing a cell construction and a joint layer of a honeycomb structure.

Figure 5 is a perspective view showing one example of a test piece cut out of a honeycomb structure.

Figure 6 is an explanatory view showing an example of a four-point bending test.

Best Mode for Carrying out the Invention

[0017] The present invention will now be described in further detail with reference to an embodiment shown in the accompanying drawings. The present invention is not limited to this embodiment.

[0018] Figures 1(a), 1(b), 1(c) and 1(d) are explanatory views showing various division patterns of honeycomb segment of a honeycomb structure in accordance with the present invention.

[0019] In Figures 1(a), 1(b), 1(c) and 1(d), reference numeral 10 denotes a honeycomb structure. The honeycomb structure 10 is made up of two or more honeycomb segments 11 and joint layers 12 for joining these honeycomb segments 11. Though not shown in detail, the honeycomb segment 11 has a large number of through channels 15 which are partitioned by walls 14 and penetrate in the axial direction. The wall 14 of the through channel 15 has a filtering function, and the construction is such that one end is clogged for predetermined through channels 15, and the other end is clogged for the remaining through channels 15.

[0020] In the honeycomb structure in accordance with the present invention, the Young's modulus of a material forming the joint layer 12 is made preferably 20% or less more preferably 1% or less of the Young's modulus of a material forming the honeycomb segment 11, or the material strength of the joint layer 12 is made lower than the material strength of the honeycomb segment 11. By specifying the Young's modulus of materials of the joint layer 12 and the honeycomb segment 11, a honeycomb structure in which a less thermal stress occurs during the use, and durability such that no crack develops is ensured can be provided. Also, even in the case where the Young's modulus of the joint layer 12 exceeds 20% of the Young's modulus of the honeycomb segment 11, if the material strength of the joint layer 12 is lower than the material strength of the honeycomb segment 11, a crack develops only in the joint layer 12, and the honeycomb segment 11 is not damaged, so that the honeycomb structure maintains a sufficient function.

[0021] Herein, the Young's modulus of the joint layer 12 and the Young's modulus of the honeycomb segment 11 means the Young's modulus of each material itself thereof, that is, the physical property inherent in the material.

[0022] Also, the definition of "the material strength of the joint layer is lower than the material strength of the honeycomb segment" will be explained below with reference to Figures 5 and 6.

[0023] A test piece 20 cut out of the honeycomb structure in accordance with the present invention as shown in Figure 5 is prepared. The test piece 20 is cut so that the length in the direction perpendicular to the through channel is 40 mm or larger and the joint layer 12 is located in the center thereof. In the present invention, the fact that in a four-point bending test (in conformity to JIS R1601) as shown in Figure 6 of the test piece 20, the probability that a fracture occurs within the joint layer 12 or at the interface between the joint layer 12 and the honeycomb segment 11 is 50% or higher is defined as the aforementioned "the material strength of the joint layer is lower than the material strength of the honeycomb segment".

[0024] Also, it is preferable that in this honeycomb structure, a portion having an area of at least 30% of the surface area of the honeycomb segment 11 in contact with the joint layer 12 have average surface roughness R_a exceeding 0.4 micron. Thereby, the two or more honeycomb segments 11 are joined more firmly, and a fear of peeling off at the time of use can almost be dispelled. The aforementioned surface roughness R_a is further preferably be 0.8 microns or more.

[0025] Also, the ratio of the total heat capacity of all the joint layers in the honeycomb structure to the total heat capacity of all the honeycomb segments constituting the honeycomb structure is preferably made 30% or lower, more preferably 15% or lower. Thereby, when the carbon particulates collected at the time of regeneration are burned to be disposed of (filter regeneration), the time taken for the rise in temperature can desirably be kept in the allowable range.

[0026] Further, it is preferable that in the honeycomb structure in accordance with the present invention, a corner portion of a cross-sectional shape of honeycomb segment in the cross section perpendicular to the through channel of honeycomb structure be rounded with a radius of curvature of 0.3 mm or larger, or be chamfered 0.5 mm or more because the occurrence of thermal stress at the time of use is reduced and great durability such that no crack develops can be given to the honeycomb structure.

[0027] Still further, in the present invention, it is preferable that the ratio of the total cross-sectional area of the joint layers to the cross-sectional area of the honeycomb structure in the cross section perpendicular to the through channel of honeycomb structure be 17% or lower, more preferably 8% or lower. The explanation of this is given with reference to Figure 3. Referring to Figure 3, in the circular honeycomb structure 10 having a cross section with diameter D , the total cross-sectional area S_H of the honeycomb structure 10 is expressed by the following formula.

$$S_H = (\pi/4) \times D^2$$

On the other hand, the total cross-sectional area S_S of the joint layers 12 is the total area of hatched portion A in Figure 3 (cross-sectional portion of the joint layers 12).

[0028] Herein, the ratio of S_S/S_H should preferably be 17% or lower from the viewpoint of the decrease in pressure loss of fluid.

[0029] Also, in the present invention, it is preferable that the ratio of the sum of the cross-sectional areas of joint layers to the sum of the cross-sectional areas of walls in the cross section of honeycomb structure perpendicular to the through channel of honeycomb structure be 50% or lower, more preferably 24% or lower. Referring to Figure 4, taking the sum of the cross-sectional areas (hatched portion B) of the joint layers 12 in the cross section of the honeycomb structure 10 as S_S , and taking the sum of the cross-sectional areas (meshed portion C) of the walls 14 as S_C , the ratio of S_S/S_C should preferably be 50% or lower from the viewpoint of the decrease in pressure loss of fluid.

[0030] Further, in the present invention, it is preferable that the ratio of the cross-sectional area of joint layer to the cross-sectional area of wall in the cross section of honeycomb structure perpendicular to the through channel of honeycomb structure be higher in the central portion and be lower on the outer peripheral side. According to such configuration, the quantity of collected carbon particulates per unit volume is smaller in the vicinity of the center than in the vicinity of the outer periphery, so that at the time of regenerating treatment at which carbon particulates are burned (regenerative combustion time), the calorific value in the vicinity of the center, where high temperatures are liable to be generated, can be kept low. Moreover, the joint layer in the vicinity of the center is dense, so that the heat capacity in that portion can be increased. For these reasons, the increase in temperature in the vicinity of the center can be kept low. As a result, a difference in temperature between the central portion and the outer peripheral side can be decreased, so that the thermal stress in the honeycomb structure can desirably be decreased.

[0031] In the present invention, the cross section perpendicular to the through channel of honeycomb structure can take various shapes such as circle, ellipse, and racetrack.

[0032] Also, the honeycomb segment constituting the honeycomb structure in accordance with the present invention preferably has a main crystal phase of one kind selected from a group consisting of cordierite, SiC, SiN, alumina, mullite, and lithium aluminum silicate (LAS) from the viewpoint of strength, heat resistance, and the like. Silicon carbide (SiC), which has a high coefficient of thermal conductivity, is especially preferable because heat can be dissipated easily.

[0033] The cell density of honeycomb segment is preferably 6 to 1500 cells/in² (0.9 to 233 cells/cm²), further preferably 50 to 400 cells/in² (7.8 to 62 cells/cm²). If the cell density is lower than 6 cells/in², the strength and effective GSA (Geometrical Surface Area) are insufficient as the honeycomb segment. If the cell density is higher than 1500 cells/in², the pressure loss increases when gas flows.

[0034] Also, the cross-sectional shape of through channel (cell shape) in the honeycomb structure is preferably any of triangle, quadrangle, and hexagon from the viewpoint of manufacture.

[0035] Also, as a material of joint layer that joins the honeycomb segment to each other, ceramic fiber, ceramic powder, cement, or the like, which has heat resistance, are preferably used singly or by being mixed. Further, as

necessary, an organic binder, an inorganic binder, etc. may be used by being mixed. The material of joint layer is not limited to the above-described materials.

[0036] The honeycomb structure in accordance with the present invention has a construction such that, as described above, it has a large number of through channels which are partitioned by walls and penetrate in the axial direction; the wall of the through channel has a filtering function; and one end is clogged for predetermined through channels, and the other end is clogged for the remaining through channels. Therefore, the honeycomb structure can be suitably used as a filter which collects and removes particulate matters contained in a dust-containing fluid, such as a particulate filter for a diesel engine.

[0037] Specifically, if a dust-containing fluid is caused to pass through one end face of the honeycomb structure having such a construction, the dust-containing fluid enters a through channel in the honeycomb structure whose end on the one end face side is not clogged, and passes through the porous wall having a filtering function to enter another through channel in the honeycomb structure whose end on the other end face side is not clogged. When passing through the wall, particulate matters in the dust-containing fluid are collected to the wall, and the purified fluid from which particulate matters have been removed is discharged from the other end face of honeycomb structure.

[0038] If the collected particulate matters accumulate on the wall, the wall is clogged, so that the function as a filter decreases. Therefore, the honeycomb structure is heated periodically by heating means such as a heater to burn and remove the particulate matters, by which the filtering function is regenerated. To accelerate the combustion of particulate matters at the time of regeneration, a metal having a catalytic function, as described later, may be carried on the honeycomb segment.

[0039] On the other hand, in the case where the honeycomb structure in accordance with the present invention is used to purify exhaust gas from a heat engine such as an internal combustion engine or to reform a liquid fuel or a gas fuel as a catalyst carrier, a metal having a catalytic function is carried on the honeycomb segment. As a typical metal having a catalytic function, Pt, Pd, and Rh are cited. At least one kind of these metals is preferably carried on the honeycomb segment.

[0040] Hereunder, the present invention will be described in further detail with reference to examples. The present invention is not limited to these examples.

[Examples 1 to 10, Comparative example 1]

[0041] Honeycomb structures measuring 144 mm in diameter and 153 mm in length having various division constructions were manufactured using a SiC-made honeycomb segment having a wall thickness of 0.38 mm, a cell density of 200 cells/in² (31 cells/cm²), and a thickness of outer peripheral portion of 0.5 mm, and using a mixture of ceramic fiber, ceramic powder, and organic and inorganic binders as the joint layer. The division construction and the properties such as the Young's modulus of material of the obtained honeycomb structure are given in Table 1. Also, the surface roughness given in Table 1 indicates the average surface roughness of the whole surface of honeycomb segment in contact with the joint layer.

[0042] This honeycomb structure is a particulate filter for purifying exhaust gas from a diesel engine, which has a construction such that one end is clogged for predetermined through channels, and the other end is clogged for the remaining through channels. The fluid pressure loss test and the regeneration test were conducted on these honeycomb structures. The results are given in Table 1.

[Table 1]

	Example 1	Example 2	Example 3	Example 4	Example 5	Example 6	Example 7	Example 8	Example 9	Example 10	Comparative example 1
Division construction	(a)	(b)	(b)	(b)	(c)	(c)	(c)	(d)	(d)	(c)	Integrated product
Young's modulus of wall material (GPa)	42	42	42	42	42	42	42	42	42	42	42
Young's modulus of joint layer material (GPa)	0.4	4	4	4	8	8	8	4	30	30	-
Young's modulus of joint layer/Young's modulus of wall (%)	1	10	10	10	19	19	19	10	71	71	-
Segment corner	R0.3	Acute angle	R0.3	R0.3	R0.3	R0.3	R0.3	R0.3	R0.3	R0.3	-
Quantity of regeneration foot: Large	Absent	Present	Present	Present	Present	Present	Present	Present	Absent	Absent	Present
Quantity of test (segment crack) foot: Standard	Absent	Present	Absent	Absent	Absent	Absent	Absent	Absent	Absent	Absent	Present
Segment surface roughness (Ra μm)	0.8	0.8	0.3	0.3	0.8	0.8	0.8	0.8	0.8	0.8	-
Axial shift after test	Absent	Absent	Present	Present	Absent	Absent	Absent	Absent	Absent	Absent	-
Wall thickness (mm)	0.38	0.38	0.38	0.38	0.38	0.38	0.38	0.38	0.38	0.38	0.38
Joint layer thickness (mm)	2	2	2	2	4	2	5	2	1	2	2
Joint layer area/structure area (%)	3.5	4.4	4.4	4.4	17	8.5	21	5.3	4.3	8.5	-
Joint layer area/wall area (%)	9.7	12.2	12.2	12.2	50	24.5	70.5	14.7	12.3	14.5	-
Result of fluid pressure loss test	Allowable range	Allowable range	Allowable range	Allowable range	Allowable range	Allowable range	High	Allowable range	Allowable range	Allowable range	Allowable range
Regeneration time	Allowable range	Allowable range	Allowable range	Allowable range	Allowable range	Allowable range	Long	Allowable range	Allowable range	Allowable range	Allowable range
Heat capacity ratio (%)	6	7	7	7	30	15	42	9	8	15	-
Joint layer strength (with respect to segment strength)	High	High	High	High	High	High	High	High	Low	Low	-

[Evaluation]

[0043] As is apparent from the results given in Table 1, when the requirements specified in the present invention were satisfied, the pressure loss of fluid was not so high, being within the allowable range (10 kPa), and the regeneration time was within the allowable range (15 min).

Industrial Applicability

[0044] As described above, the honeycomb structure in accordance with the present invention achieves a remarkable effect that a less thermal stress occurs during the use; durability such that no crack develops is ensured; a difference in temperature between the central portion and the outer peripheral portion hardly occurs; and moreover the pressure loss of fluid is low.

Claims

1. A honeycomb structure comprising two or more honeycomb segments each of which has a large number of through channels which are partitioned by walls and penetrate in axial directions, the wall of said through channel having a filtering function, and is constructed so that one end is clogged for predetermined through channels, and the other end is clogged for the remaining through channels, and a joint layer for joining said two or more honeycomb segments to each other, **characterized in that**
 either that the Young's modulus of material of said joint layer is 20% or less of the Young's modulus of material of said honeycomb segment, or that the material strength of said joint layer is lower than the material strength of said honeycomb segment is satisfied.
2. The honeycomb structure according to claim 1, **characterized in that** a portion having an area of at least 30% of the surface area of said honeycomb segment in contact with said joint layer has an average surface roughness Ra exceeding 0.4 micron.
3. The honeycomb structure according to claim 1 or 2, **characterized in that** the ratio of the total heat capacity of all the joint layers in said honeycomb structure to the total heat capacity of all the honeycomb segments constituting said honeycomb structure is 30% or lower.
4. The honeycomb structure according to any one of claims 1 to 3, **characterized in that** a corner portion of the cross-sectional shape of said honeycomb segment in a cross section perpendicular to the through channel of said honeycomb structure is rounded with a radius of curvature of 0.3 mm or larger, or is chamfered 0.5 mm or more.
5. The honeycomb structure according to any one of claims 1 to 4, **characterized in that** the ratio of the total cross-sectional area of said joint layers to the cross-sectional area of said honeycomb structure in a cross section perpendicular to the through channel of said honeycomb structure is 17% or lower.
6. The honeycomb structure according to any one of claims 1 to 5, **characterized in that** the ratio of the sum of the cross-sectional areas of said joint layers to the sum of the cross-sectional areas of said walls in a cross section of honeycomb structure perpendicular to the through channel of said honeycomb structure is 50% or lower.
7. The honeycomb structure according to any one of claims 1 to 6, **characterized in that** said honeycomb segment has a main crystal phase of one kind selected from a group consisting of cordierite, SIC, SIN, alumina, mullite, and lithium aluminum silicate (LAS).
8. The honeycomb structure according to any one of claims 1 to 7, **characterized in that** said honeycomb segment carries a metal having a catalytic function so as to be used to purify exhaust gas from a heat engine or combustion equipment or to reform a liquid fuel or a gas fuel.
9. The honeycomb structure according to claim 8, **characterized in that** said metal having a catalytic function is at least one kind of Pt, Pd, and Rh.
10. The honeycomb structure according to any one of claims 1 to 9, **characterized in that** the cross-sectional shape of said through channel in said honeycomb segment is any of triangle, quadrangle, and hexagon.

FIG. 1 (a)




FIG. 1 (b)




FIG. 1 (c)




FIG. 1 (d)




FIG. 2




FIG. 3




FIG. 4




FIG. 5





FIG. 6



INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP01/00076

A. CLASSIFICATION OF SUBJECT MATTER Int.Cl ⁷ B01D 46/00, 53/86, B01J 35/04, F01N 3/28		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) Int.Cl ⁷ B01D 46/00, 53/86, B01J 35/04, F01N 3/28		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Jitsuyo Shinan Koho 1926-1996 Toroku Jitsuyo Shinan Koho 1994-2000 Kokai Jitsuyo Shinan Koho 1971-2000 Jitsuyo Shinan Toroku Koho 1996-2000		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X Y	US, 5914187, A (IBIDEN CO LTD), 22 June, 1999 (22.06.99), Full text & JP, 8-28246, A & WO, 9725203, A1 & EP, 816065, A1	1,3,5-7,10 8,9
PX PA	JP, 2000-279729, A (IBIDEN CO., LTD.), 10 October, 2000 (10.10.00), Claims (Family: none)	2 4
Y	JP, 9-158710, A (Denso Corporation), 17 June, 1997 (17.06.97), Claims (Family: none)	8,9
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search 02 March, 2001 (02.03.01)		Date of mailing of the international search report 13 March, 2001 (13.03.01)
Name and mailing address of the ISA/ Japanese Patent Office		Authorized officer
Facsimile No.		Telephone No.

Form PCT/ISA/210 (second sheet) (July 1992)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.